



EUROPEAN
SEALING
TECHNOLOGY
Seals for industry

Rue adolphe Fisher, 140
L-1521 Luxembourg
Tél. : +352 26845676
Fax : +352 26845677
info@est-seals.eu

EPDM SHEET PRODUCT

PROPERTIES

Type

Ethylene Propylene Rubber, EPR, EPT, EPDM

Colour

Black

Hardness

60° (+/-5°) Shore 'A'

Specific Gravity

1.28 g/cm³

Tensile Strength

≥ 7MPa

Elongation at Break

≥ 400%

Tear Resistance

≥ 20 N/mm

Temperature Range**In air :**

-30°C to 100°C

In Oil:

Not recommended

In water/Steam:

Max 90°C

Chemicals and physicals characteristics

Advantages in performance...

Capability to recover after deformation (compression set), steam resistance, ozone weather and sunlight resistance, air ageing and oxidation resistance.

EPDM is suitable for some acids and alkalis, alcohol's, aldehydes, brake fluids, esters, ketones, and silicone oils, polar solvents.



Rue adolphe Fisher, 140
L-1521 Luxembourg
Tél. : +352 26845676
Fax : +352 26845677
info@est-seals.eu

Limitations in performance...

EPDM is not suitable for... in diester oils, petroleum based fuels & oils including aliphatic hydrocarbons, aromatic & non-aromatic hydrocarbons, extended or oxygenated fuels. as well as halogenated solvents, halogenated hydrocarbons, lacquer solvents, LP gases & fuels, mineral oils, refrigerant halo fluorocarbons with oil... EPDM is also not recommended for its flame resistance, air ageing and ozone at high temperature (+ 130°C; peak).